

POLYCORP C-600

Chemical Cure Activator

May 2016

Polycorp C-600 Chemical cure activator for all rubber linings. Suitable for use with autoclave, open steam and chemical cures. FDA compliant as per 21CFR177.2600.

TYPICAL PROPERTIES:

	C-600
Composition	A mixture of rubber chemicals dissolved in an organic solvent.
Color	Yellowish liquid
% NV by weight	31.1 %
Weight /gal.	8.07 +/- 0.30 lbs
Theoretical Coverage	300 sq. ft /gal.
Shelf Life	18 months from date of manufacture, unopened container 70°F- 80°F (21°C - 27°C) storage temperature

Application:

Polycorp C-600 cement can be applied by brush or roller. Once the rubber lining is installed, coat the surface of lining with 3 coats of C-600 allowing 30-45 minutes drying time between each coats. After the last coat has been applied wait for 24 hours to allow chemical to penetrate the lining before applying any heat source.

Safety:

Before using this product please refer to the Safety Data Sheet (SDS) for safe use and handling.