## **TECHNICAL DATA SHEET**

C-90/C-91 Page 1 of 1



## POLYCORP C- 90/C-91

Chemlok 289/290 May 2014

**Polycorp C-90/C-91** is a primer/cover coat adhesive system manufactured by Lord (Chemlok<sup>®</sup> 289/290). It is used in lining operations to bond rubber linings to steel. It provides excellent corrosion resistance and is suitable for use with autoclave, open steam and chemical cures.

TYPICAL PROPERTIES:	CHEMI OK 289/C-90 PRIMER	CHEMLOK 290/C-91 COVER-COAT

Composition A mixture of polymers, organic compounds and fillers dissolved

in an organic solvent system.

Color Green Liquid Red Liquid

% NV by weight 23.0 – 26.0% 5.5 – 7.5%

Viscosity @ 77 F

Zahn #1 30 – 55 sec.

Zahn #4 20 – 40 sec.

Weight/Gal. 7.7 – 8.0 lb/gal 7.2 – 7.4 lb/gal

Solvents MEK, Xylene, IPA Toluene

Theoretical Coverage 300 sq. ft./gal 300 sq.ft./gal.

Shelf Life One year from date of shipment, unopened container

70°F-80°F (21°C-26°C)

## Application:

Both primer and cover-coat can be applied using a roller or brush. Thoroughly stir Primer and Cover-coat before using and agitate sufficiently during use to keep dispersed solids uniformly suspended. Please refer to section 6 of application manual for general application instructions. Complete product information available @ www.lord.com

## Safety:

Before using this product please refer to the Material Safety Data Sheet (MSDS) for safe use and handling.







<sup>\*</sup>Typical properties based on technical data sheet from Lord. Product information available @ www.lord.com